The LONGWAY General Series 2V batteries (100-3000Ah) are designed and developed using AGM technology and valve controlled sealing technology. They can meet conventional performance requirements, with a designed float charging life of over 15 years. The valve controlled non-spillable structure design allows safe use in any direction and is certified by sea and air freight. The battery performance also meets international standards. such as IEC60896-2012, UL1989.etc.



General Feature

- High reliability, safe without leakage, can be used in any position
- Excellent recovery performance after deep discharge
- Environmentally friendly products.
 Meet EU battery directive RoHS and REACH standards
- · Maintenance free
- Widely applicable temperature range, can be used at -20 °C~60°C
- Low self-discharge rate. The average monthly self-discharge rate of the battery is less than 2.5%

(It is recommended to recharge after storage for 6 months or before use)


Applications

- Electrical power system
- Solar system
- · Electrical test equipment
- Telecom & Network Equipment
- UPS, fire alarm & safe-protection
- Emergency lighting device; Alarm system
- · Robots and control machines and other

Performance

Nominal Voltage	2V (1cell)					
Capacity	@25 °C					
10hr Rate (40.0A)	440Ah @ to 1.75V/ceII					
5hr Rate (68.0A)	300Ah @ to 1.70V/cell					
3hr Rate (100A)	300Ah @ to 1.60V/ceII					
Weight	Approx (25.5 \pm 3%)kg (56.22lbs)					
Internal Resistance	Approx $0.60 m\Omega$ fully charged $@25^{\circ}{ m C}$					
Maximum Discharge Current	400A(3sec)					
Terminal	17					
Operating Temperature Range	Discharge:-20℃~60℃;Charge:0℃~50℃ Storage:-20℃~40℃					
Container Material	ABS(UL94 HB)/UL94-V0 Optional					

Dimensions







Length	211mm	8.31inch		
Width	175mm	6.89inch		
Height	336mm	13.2inch		
Totalheight	365mm	14.4inch		

Battery use

Cycle use

- 1. Limit the initial charging current to no more than 100A
- 2. Keep charging voltage at 2.40-2.50V/unit.and continue charging at least 3 hours after the charging current reduces to 8A to ensure full charge
- 3. The compensation coefficient of charging voltage and temperature is -5mv/cell/ $^{\circ}$

Float use

- 1. Limit the initial charging current to no more than 100A
- 2. Keep charging voltage at 2.25-2.30V/unit.When the voltage reaches the constant voltage, the current gradually decreases until the battery is fully charged and continues to charge
- 3. The compensation coefficient of charging voltage and temperature is -3mv/cell/ $\!\!\!\!^{\rm C}$








Kaiying Power Supply & Electrical Equip Co., Ltd Email: sales@longwaybattery.com Tel:0595-68782266 Fax:0595-68782222 Website: http://www.longwaybattery.com Add: Kaiying Industrial Area, Chengxiang Town, Anxi, Quanzhou, Fujian Province, China KY-IOP-LW2-400 B0. May 2023




General VRLA Battery FM400G (2V400Ah)







Floating Charging Characteristics Diagram




Cycle Life




Cycle charging characteristic diagram



Temperature and capacity characteristics



Self-discharge characteristic



Constant current characteristics(A,25°C)

F.V/TIME	15min	30min	60min	2h	3h	5h	8h	10h	20h	100h
1.60	540	420	224	148	107	75.1	52.8	42.6	21.3	5.08
1.65	529	412	220	147	106	74.7	52.5	42.5	21.3	5.07
1.70	518	403	215	147	106	74.4	52.3	42.3	21.1	5.03
1.75	502	391	208	146	105	74.0	52.0	42.1	21.1	5.02
1.80	492	383	204	143	103	72.5	49.4	42.0	21.0	5.00

Constant power discharge characteristic (W,25℃)

F.V/TIME	15min	30min	60min	2h	3h	5h	8h	10h	20h	100h
1.60	972	777	429	273	211	149	105	85.3	42.6	10.2
1.65	953	761	420	271	210	149	105	85.1	42.5	10.1
1.70	933	746	412	270	209	148	104	84.5	42.3	10.1
1.75	904	723	399	269	208	147	104	84.3	42.1	10.0
1.80	886	709	391	263	204	144	98.6	84.0	42.0	10.0







Kaiying Power Supply & Electrical Equip Co., Ltd Email: sales@longwaybattery.com Tel:0595-68782266 Fax:0595-68782222 Website: http://www.longwaybattery.com Add: Kaiying Industrial Area, Chengxiang Town, Anxi, Quanzhou, Fujian Province, China KY-IOP-LW2-400 B0. May 2023