

PRODUCT DATA SHEET

USZ Friction Reducer for Oil Well Cementing**Product Description**

USZ drag reducing agent (dispersing agent) can adjust the electric charge on the surfaces of cement particles to get proper cement rheology. As a result, it can reduce pump pressure, enhance drilling efficiency and used in construction easily.

Characteristics

- USZ is modified polymer which made up of methanal and acetone.
- The normal dosage is: 0.3%~0.8% USZ (BWOC), and it is not confined to this range in some particular case.
- Soluble easily
- Increasing additive dosage, it can adjust the rheology of the cement slurry effectively, and reduce the consistency.
- With good high temperature resistance, it can be used within 30℃~180℃ (BHCT).
- Consolidate cement stones, enhance its compression strength and control fluid loss.
- With certain retarding property.
- Mixed with or without water.
- Good compatibility with other additives.

Technical Specification

Items	Specification
Appearance	No hardened particles or powder
Fineness (0.315mm sieve),%	<15.0
Thickened linear(85℃,70.3MPa,44min),Bc	Normal
Ratio of thickening time(85℃,70.3MPa,44min)	1.0 - 2.0
Rheology(85℃,0.1MPa)	n K,Pa.s ⁿ
Ratio of compression strength(110℃,21MPa,24h)	≥ 0.50 ≤ 0.70 ≥ 0.80
1. The ratio of thickening time: refers to the ratio of thickening time of cement slurry with drag reducer to the thickening time of pure cement slurry.	
2. The ratio of compression strength: refers to the ratio of the compression strength of cement stone with drag reducer to the thickening time of pure cement paste.	

Packing, Storage

- USZ sacked with three-layer plastics bag, 25kg per bag.
- Be kept away from moisture and possible damage of the packages in transportation, and stored in cool and dry situation. Storage life time is two years.

Email:info@oilchemleader.com

Website:www.oilchemleader.com