

### TYPICAL PROPERTIES of REXOLITE®

ASTM OR UL TEST	PROPERTY	REXOLITE® 1422
-	Acoustic Impedance	2.5
D696	Coefficient of Linear Thermal Expansion (x 10 <sup>-5</sup> in./in./°F)	3.8
D792	Density (lb/in <sup>3</sup> ) (g/cm <sup>3</sup> )	0.038 1.05
D150	Dielectric Constant (1 MHz to 500 GHz)	2.53
D149	Dielectric Strength (V/mil) short time, 1/8" thick	500
D150	Dissipation Factor at 1 MHz at 10 MHz at 10 GHz	0.00012 0.00025 0.00066
D638	Flexural Strength (psi)	11,500
D256	IZOD Notched Impact (ft-lb/in)	0.3
-	Optical Transmittance, Visible Light	87%
D648	Recommended Operating Temperature Range (°F) (°C)	-76 to +212 -60 to +100

ASTM OR UL TEST	PROPERTY	REXOLITE® 1422
-	Refractive Index @ 589 nM @ 486 nM @ 656 nM	1.59 1.604 1.585
D257	Surface Resistivity (ohm-cm)at 50% RH	>10 <sup>14</sup>
D638	Tensile Strength (psi)	9,000
C177	Thermal Conductivity (BTU-in/ft <sup>2</sup> -hr-°F) (x 10 <sup>-4</sup> cal/cm-sec-°C)	1.01 3.5
-	Velocity of Sound (in/sec)	93,000
-	Velocity of Sound (in/sec)	93,000
D257	Volume Resistivity (ohm-cm)at 50% RH	>10 <sup>16</sup>
D570	Water Absorption, 24 hrs (%)	0.08